

GGFAST IMP

Polymer based wet rubbing fastness improver

PROPERTIES :

- Yellow Liquid
- Special polymer mixture used especially to improve rubbing fastness.
- Prevents the release of dye by covering the fibers in the fabric structure.
- Minimizes the loss of the fixed dye on the fiber after the process.
- Not affected by electrolytes
- It can be easily diluted with cold water
- Does not affect color and light fastness
- Does not cause back-contamination

It can be applied with cold water, compatibility with different finishing chemicals should be checked before use.

For Cotton, Polyamide, Viscose fabrics

APPLICATION :

Foulard application: 15 – 30 g/l GGFAST IMP 130°C-160°C 1-2min
pH: 4.5 – 5.5

For wool, linen etc fabrics

Foulard application:

30 – 60 g/l GGFAST IMP 130°C-160°C 1-2min
pH: 4.5 – 5.5

Denim wash:

3-5% GGFAST IMP

30 - 40 °C 5 – 10 minutes

Tumbler Dryer 80 - 95 °C

Direct Dyes 2%		Reactive Dyes 4%		Indigo Denim		Vat Dyes		Pigment Printing	
Dry	Wet	Dry	Wet	Dry	Wet	Dry	Wet	Dry	Wet
4 - 5	3-4	4 - 5	3	3-4	1-2	4 - 5	3	4	3 - 4
GGFAST IMP									
Dry	Wet	Dry	Wet	Dry	Wet	Dry	Wet	Dry	Wet
4 - 5	4 - 5	4 - 5	4-5	4 - 5	3	4 - 5	4 - 5	4 - 5	4-5

Storage :

The product sensitive to frost and heat and must not be stored at temperature below 0°C or above 40°C. Irreparable damage is possible. In case of suspected frost or heat damage , the usability of the product has to be checked before processing.

Attention :

The above recommendations are based on comprehensive studies and experience made in practical finishing. They are, however, without liability regarding property rights of third parties and foreign laws. The user should test for himself whether the product and the application are suited for his very special purposes. We are, above all, not liable for fields and methods of application which have not been put down by us in writing. Advice for marking regulations and protective measures can be taken from the respective safety data sheet.

GG Chem :

Ulas Ergene 2 OSB Mah. D100 Cad. No.2 Ergene –Tekirdağ- TÜRKİYE
Phone : +90 507 923 9808 Mail: info@ggchemical.net
www.ggchemical.net